



PRODUCT DATA SHEET

Gillfab™ 1367A/C

DESCRIPTION

Gillfab™ 1367A is a rigid, high impact and fire resistant fiberglass reinforced phenolic laminate. Gillfab™ 1367C is the product designation for Gillfab™ 1367A supplied in roll stock. Gillfab™ 1367A and 1367C are economical alternatives to the other Gillfab™ 1367 series for general purpose application where weight is not a critical concern.

APPLICATIONS

Cargo liners for cargo compartment, bulkhead facings and blowout panels for aircraft. Also used as backing material for non-textile floor mats used in wet areas of cabin interior (without Tedlar® overlay).

FEATURES

- High impact strength
- Fire resistant
- Corrosion resistant
- Low moisture absorption
- Low smoke and toxicity generation
- Service temperature -40°F to 220°F (-40°C to 110°C)

AVAILABILITY



	Gillfab™ 1367A (Sheet form)	Gillfab™ 1367C (Roll form)
Thickness inch (mm)	0.013 (0.330)	0.013 (0.330)
	0.020 (0.508)	0.020 (0.508)
	0.025 (0.635)	0.030 (0.762)
	0.030 (0.762)	0.040 (1.016)
	0.040 (1.016)	
	0.045 (1.143)	
Length	Standard 144 inch (3,658 mm)	Standard 150 feet (45,720 mm)
	Maximum 168 inch (4,267 mm)	Maximum 150 feet (45,720 mm)
Width	Standard 48 inch (1,219 mm)	Standard 48 inch (1,219 mm)
	Maximum 72 inch (1,829 mm)	Maximum 60 inch (1,524 mm)

	Sides	Standard	BMS 8-223, GR C	DMS 2419, CL 2	Available Upon Request
Color	Face side	1 mil White Tedlar®	2 mil Beige Tedlar®	Amber	Granite Grey Desert Sand
	Back side	Amber	Amber	Amber	Amber

CONSTRUCTION

- Reinforcement:** Woven fiberglass cloth
- Resin System:** Phenolic
- Surface Finish:** 1 mil white Tedlar® overlay for standard applications



ALTERNATIVE GILLFAB™ 1367 PRODUCTS

Gillfab™ 1367 series are high strength, high impact and fire resistant fiberglass reinforced phenolic laminates for aircraft cargo liner applications.

TGC Product No.	Difference
Gillfab™ 1367	Slightly higher impact values than 1367A, and offering additional thickness.
Gillfab™ 1367A	Economical alternative to 1367 with standard weight and thickness requirements.
Gillfab™ 1367B	Thinner and lighter than 1367A.
Gillfab™ 1367C	1367A in roll form.
Gillfab™ 1367E	1367A with 1mil white Tedlar® bonded to both faces of the laminate.
Gillfab™ 1367F	1367A molded to a "Z" shape for wire spacing in cargo bay.
Gillfab™ 1367G	Extremely thin, lightweight and superior impact strength to corresponding types.
Gillfab™ 1367M	1367B in roll form.
Gillpatch™ 1367P	Patch laminate intend for repairing facings of 1367A.

SPECIFICATIONS

Gillfab™ 1367A

- Boeing BMS 8-223, Class 2, Grade B, Types 13 through 40
- McDonnell Douglas DMS 2419 Classes 1 and 2, Types 13 through 40
- Airbus 2550 MIM 000800, Airbus Types 1 through 5
- FAR 25.853 and 25.855

Gillfab™ 1367C

- Similar to 1367A but produced in roll stock

HEALTH PRECAUTIONS

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Material Safety Data Sheet (MSDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. A MSDS is available at www.thegillcorp.com/products/msds/html.

For industrial use only. Keep away from children. Additional information can be found at: www.thegillcorp.com. For sales and ordering information call 1-626-443-6094.

PERFORMANCE PROPERTIES, TYPICAL

The following tests are run in accordance with BMS 8-223, DMS2419, A12250 MIM000800 and HMS E2-001 specification requirements.

TGC Part Number	1367A013 1367C013	1367A020 1367C020	1367A025 N/A	1367A030 1367C030	1367A040 1367C040	1367A045 N/A	1367A060 N/A
Thickness, inch (mm)	0.013 (0.33)	0.020 (0.51)	0.025 (0.64)	0.030 (0.76)	0.040 (1.02)	0.045 (1.14)	0.060 (1.52)
Weight, psf (kg/m ²)	0.12 (0.59)	0.20 (0.98)	0.25 (1.22)	0.29 (1.42)	0.38 (1.86)	0.44 (2.15)	0.56 (2.73)
Impact Strength, ft-lbs (N-m)	11 (15) ¹	15 (20) ¹	18 (24) ²	19 (26) ¹	25 (34) ¹	25 (34) ²	32 (44) ²
Bolted Joint Strength, lbs (N)	Warp	225 (1,003)	254 (1,131)	N/A	312 (1,388)	385 (1,713)	N/A
	Fill	233 (1,038)	261 (1,163)	N/A	314 (1,397)	390 (1,736)	N/A
Double Point Edge Bearing, lbs (N)	Warp	315 (1,401)	N/A	N/A	N/A	N/A	N/A
	Fill	310 (1,379)	N/A	N/A	N/A	N/A	N/A
Flammability	Meets FAR 25.853 & 855 Appendix F Part I & III						
Tedlar® Peel Separation, inch	No Tedlar® Peel Separation						

¹BSS 7326; ²ASTM D 5420 Figures shown reflect typical values and should not be used as design specifications.

All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.