



PRODUCT DATA SHEET

Gilliner™ 1066/1066R

DESCRIPTION

Gilliner™ 1066 is a general purpose laminate made from fiberglass cloth reinforced polyester resin. Gilliner™ 1066 is available with a 1 mil white Tedlar® overlay (Gilliner™ 1066T) on the face side or with bondable surface panel facings (Gilliner™ 1066S). Gilliner™ 1066 comes in sheet or roll stock. Request Gilliner™ 1066R for thicknesses under 0.060 inch (1.52 mm).

APPLICATIONS

The laminate is designed for general purpose aircraft cargo compartment liner.

FEATURES

- Good impact strength
- Puncture and corrosion resistant
- Service temperature to: 180°F (80°C)

AVAILABILITY

	Gilliner™ 1066 (Sheet form)	Gilliner™ 1066 (Roll form)
Thickness, inch (mm)	0.010 (0.254)	0.010 (0.254)
	0.016 (0.406)	0.016 (0.406)
	0.023 (0.584)	0.023 (0.584)
	0.030 (0.762)	0.030 (0.762)
	0.045 (1.143)	0.045 (1.143)
	0.060 (1.524)	0.060 (1.524)
	0.070 (1.778)	
	0.075 (1.905)	
	0.090 (2.286)	
	0.125 (3.175)	
Length, inch (mm)	Standard 144 (3,658)	Standard 150 feet (45,720)
	Maximum 168 (4,267)	Maximum 150 feet (45,720)
Width, inch (mm)	Standard 48 (1,219)	Standard 48 (1,219)
	Maximum 60 (1,524)	Maximum 60 (1,524)



CONSTRUCTION

Resin System: Polyester resin
Reinforcement: Woven fiberglass cloth

ALTERNATIVE GILL PRODUCTS

TGC Product No.	Difference
Gilliner™ 1366T	Fiberglass/polyester laminate with higher impact strength and puncture resistance.

SPECIFICATIONS

- Proprietary - FAR 25.855 Flammability



HEALTH PRECAUTIONS

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Material Safety Data Sheet (MSDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. A MSDS is available at www.thegillcorp.com/products/msds/html.

For industrial use only. Keep away from children. Additional information can be found at: www.thegillcorp.com. For sales and ordering information call 1-626-443-6094.

PERFORMANCE PROPERTIES, TYPICAL

The following tests are run in accordance with DMS 1946.

TGC Product		1066-013	1066-016	1066-023	1066-030	1066-045	1066-060
Weight, psf (kg/m ²)		0.12 (0.60)	0.19 (0.91)	0.22 (1.05)	0.30 (1.42)	0.44 (2.14)	0.60 (2.80)
Edge Bearing, ksi (Mpa)	Warp	28 (193)	39 (269)	28 (193)	30 (207)	32 (221)	38 (262)
	Fill	32 (221)	34 (234)	25 (172)	32 (221)	61 (421)	43 (296)
Bolted Joint Strength, lbs (N)	Warp	258 (1,148)	169 (752)	401 (1,784)	239 (1,063)	453 (2,015)	653 (2,905)
	Fill	240 (1,068)	179 (796)	365 (1,624)	274 (1,219)	569 (2,531)	409 (1,819)
Impact Strength, ft-lbs (N-m)		6 (8)	9 (12)	11 (15)	17 (23)	25 (34)	35 (48)
Water absorption, %		1.5	1.3	1.3	1.6	2.9	2.1
Flammability		Meets FAR 25.853 & 855 Part I & III					

Figures shown reflect typical values and should not be used as design specifications.

All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.