



PRODUCT DATA SHEET

Gilliner® 1366B/1366E

DESCRIPTION

Gilliner® 1366B and 1366E are high impact resistant grade liners constructed of woven E- and S-glass cloth with a polyester resin system to optimize strength, weight and cost. This product offers superior mechanical properties and higher strength-to-weight ratio compared to all E glass constructions. 1 mil. white polyvinyl fluoride film overlay on the face side is included for Gilliner® 1366E.

APPLICATIONS

Aircraft cargo compartment liner for general purpose use.

FEATURES

- High impact strength
- Abrasion resistant
- Corrosion resistant
- Fire resistant

AVAILABILITY

Thickness, inch (mm)	0.011 (0.28)	0.050 (1.27)
	0.020 (0.51)	0.060 (1.52)
	0.030 (0.76)	0.070 (1.78)
	0.040 (1.02)	0.090 (2.29)
	0.045 (1.14)	
Length	Maximum 168 inch (4,267 mm) in sheet form Typical 150 feet (45,720 mm) in roll form	
Width, inch (mm)	Typical 48 (1,219), Maximum 72 (1,829)	
Color	Natural or White	



CONSTRUCTION

- Resin:** Polyester
- Reinforcement:** Woven E- and S-glass fiber cloth
- Surface:** 1 mil. white polyvinyl fluoride film overlay (for 1366E)

SPECIFICATIONS

- FAR Part 25, Appendix F Parts I and III (burn through)

HEALTH PRECAUTIONS

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. A SDS is available at <https://www.thegillcorp.com/msds.php>.

For industrial use only. Keep away from children. Additional information can be found at: www.thegillcorp.com. For sales and ordering information call 1-626-443-6094.



PERFORMANCE PROPERTIES, TYPICAL

The following tests are run in accordance with BMS 8-2 specification requirements.

TGC Part Number		1366B011	1366B020	1366B030	1366B045	1366B070
Thickness, inch (mm)		0.011 (0.28)	0.020 (0.51)	0.030 (0.76)	0.045 (1.14)	0.070 (1.78)
Maximum Weight, psf (kg/m ²)		0.13 (0.63)	0.21 (1.03)	0.32 (1.56)	0.50 (2.44)	0.74 (3.61)
Tensile Strength ¹ , ksi (MPa)	Warp	> 50 (340)				
	Fill					
Flexural Strength ² , ksi (MPa)	Warp	N/A			≥ 30 (210)	
	Fill					
Flexural Tangent Modulus ² , Msi (GPa)	Warp	N/A			≥ 2.5 (17)	
	Fill					
Water Absorption ³ , % Increase		< 2.0				
Bond Strength - Warp ⁴ , lbf (N)		≥ 500 (2200)				
Abrasion Resistance ⁵ , g/1000 cycles		< 0.17				
Impact Strength ⁶ , ft-lb (N-m)		13 (18)	16 (22)	20 (27)	32 (43)	47 (64)
Edge Bearing Strength ⁷ , ksi (MPa)	Warp	≥ 40 (270)				
	Fill					
Flammability		Meets FAR 25.853 & 855 Appendix F Part I & III				

Table shown reflects typical values and should not be used as design specifications.

¹Tensile Strength was tested and calculated per ASTM D638.

²Flexural Strength and Modulus were tested and calculated per ASTM D790.

³Water Absorption was tested and calculated per ASTM D570.

⁴Bond Strength was tested and calculated per ASTM D5868 using modified specimen preparation and test speed.

⁵Abrasion resistance was tested per ASTM D3389 with CS-10 Wheel, 500 grams of weight, and minor modifications to specimen preparation.

⁶Impact Strength was tested calculated per ASTM D5420 using a modified dart and specimen test frame.

⁷Edge Bearing Strength was calculated per ASTM D953 using a modified tension loading fixture.

All recommendations, statements, values and technical data herein are based on tests The Gill Corporation believes to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. Users shall rely on their own information and tests to determine suitability of the product for the intended use and assume all risks and liability resulting from their use of the product. The Gill Corporation's sole responsibility shall be to replace that portion of the product that proves to be defective. The Gill Corporation will not be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements not contained in a written agreement signed by an officer of The Gill Corporation shall not be binding upon The Gill Corporation. Gilliner® is a registered trademark of The Gill Corporation.