



# **PRODUCT DATA SHEET**

# **Gillcore® HA Honeycomb**

# DESCRIPTION

Gillcore® HA is a commercial grade meta-aramid fiber reinforced honeycomb which is coated with heat resistant phenolic resin. Gillcore® HA is an economical alternative of Gillcore® HD for non-aerospace applications. A wide selection of HA honeycomb types, including different cell sizes, cell geometries, paper thicknesses and densities are available.

## APPLICATIONS

Sports and leisure industries such as surfboards, pleasure boats, skis and auto racing bodies.

Transportation industries such as train car panels and ground transportation structures.

Special projects for marine ground antennas, navy joiner panels and military shelters.

· High toughness

· Good fatigue and impact resistance

· Good formability for curve forming

· Good dielectric properties


# **FEATURES**


- · High strength to weight ratio
- Corrosion resistance
- Fire resistant (self-extinguishing)
- Good thermal stability
- · Good thermal and electrical insulating properties

# **AVAILABILITY**

- Hexagonal Shaped Core L = Ribbon Dimension W = Dimension normal to ribbon
- T = Thickness dimension

\* BMS 8-124 Specification





#### Available in sheet form or block form

Direction/Configuration	Hexagonal Core Ribbon dimension as block width	Hexagonal Core Ribbon dimension as block length	Overexpanded Core					
L	Typical 48 inch (1,219 mm)	Maximum 96 inch (2,438 mm)	Maximum 50 inch (1,270 mm)					
(Ribbon dimension)	Maximum 65 inch (1,651 mm)							
W	Typical 96 inch (2,438 mm)	Maximum 18 inch (1 210 mm)	Maximum 96 inch (2,438 mm)					
(Dimension normal to ribbon)	Maximum 144 inch (3,658 mm)	Maximum 48 inch (1,219 mm)						
Thickness		0.200 inch (5.08 mm) - 34 inch (864 mm)						

# CONSTRUCTION

Reinforcement:	Meta-Aramid paper, commercial grade
Resin:	Phenolic

## **SPECIFICATIONS**

• FAR 25.853a - fire resistance

#### F203 - 9/21

Updated: 12/01/19




# **HEALTH PRECAUTIONS**

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. A SDS is available at https://www.thegillcorp.com/msds.php.

For industrial use only. Keep away from children. Additional information can be found at: www.thegillcorp.com. For sales and ordering information call 1-626-443-6094.

# PERFORMANCE PROPERTIES, TYPICAL

The following tests are run in accordance with BMS8-124 specification requirements.



HA Honeycomb Ho	Gillcore®		Density	Compressive			Plate Shear								
	HA Honeycomb Configuration	Cell Size		Bare		Stabilized		L Direction			W Direction				
				Strength S		Stre	ngth	n Strength		Modulus		Strength		Modulus	
		mm	kg/m <sup>3</sup>	psi	MPa	psi	MPa	psi	MPa	ksi	GPa	psi	MPa	ksi	GPa
HA-1/8-3.0	HA132	3.2	48	286	1.97	300	2.07	212	1.46	6.82	0.05	99	0.68	3.91	0.03
HA-1/8-8.0	HA182	3.2	128	1,648	11.36	1,687	11.62	513	3.54	15.88	0.11	362	2.49	9.04	0.06
HA-3/16-4.0	HA343	4.8	64	436	3.00	458	3.16	312	2.15	9.30	0.06	162	1.12	4.74	0.03
HA-1/4-2.0	HA422	6.4	21	122	0.84	185	1.27	101	0.70	4.61	0.03	55	0.38	2.96	0.02
HA-3/16-3.0-OX	HA332O	4.8	48	281	1.94	314	2.17	117	0.81	3.01	0.02	135	0.93	5.88	0.04

Other cell size and density are available upon request.

Flammability: Gillcore® HA honeycomb meets the flammability requirements of FAR 25.853 Appendix F Part I

Figures shown reflect typical values and should not be used as design specifications.

Updated: 12/01/19

All recommendations, statements, values and technical data herein are based on tests The Gill Corporation believes to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. Users shall rely on their own information and tests to determine suitability of the product for the intended use and assume all risks and liability resulting from their use of the product. The Gill Corporation's sole responsibility shall be to replace that portion of the product that proves to be defective. The Gill Corporation will not be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements not contained in a written agreement signed by an officer of The Gill Corporation shall not be binding upon The Gill Corporation.